

Record 20: JP62020543A**(ENG) POLYOLEFIN COMPOSITION****Assignee:** MITSUBISHI PETROCHEMICAL CO

[no drawing available]

Inventor(s): NISHIDA KOJI ; OKAMOTO TAKESHI ;
KITANI RYOICHI**Application No:** JP 15805185 A**Filing Date:** 19850719**Issue/Publication Date:** 19870129

Abstract: (ENG) <sec>PURPOSE: To obtain the titled composition improved in balance between moldability, impact strength, and environmental stress cracking resistance, by blending each specific ultrahigh-molecular weight ethylene polymer and ethylene- α -olefin copolymer.
CONSTITUTION: The objective composition can be obtained by blending (A) 90W10wt% of an ethylene- α -olefin copolymer with a MFR 0.1W5g/10min, density 0.9W0.94 (pref. 0.93W0.94g/cm³), and Q-value (ratio: weight-average molecular weight/number-average molecular weight) 2W8, prepared by copolymerization, using Ziegler- or Phillips-type catalyst by either gaseous phase, solution, or slurry process, between ethylene and α -olefin (pref. of 6W8C) and (B) 10W90wt% of an ethylene polymer with a MFR at 10kg load 0.1W1.5g/10min, density 0.935W0.965g/cm³, Q-value 4W16, and die swell ratio \geq 1.35. This composition has the following characteristics: MFR ... 0.03W0.5g/10min, density ...0.935W0.955g/cm³.</sec>

Priority Data: JP 15805185 19850719 A X;